## (19) World Intellectual Property Organization International Bureau





(43) International Publication Date 30 June 2005 (30.06.2005)

PCT

## (10) International Publication Number WO 2005/058488 A2

- (51) International Patent Classification?: B01J 23/10, 29/06, 37/04, C10G 11/04, 11/05, 45/04, B01J 23/06, 23/24
- (21) International Application Number:

PCT/EP2004/013913

- (22) International Filing Date: 6 December 2004 (06.12.2004)
- (25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

60/527,756 04075063.0 9 December 2003 (09.12.2003) US 9 January 2004 (09.01.2004) EP

- (71) Applicant (for all designated States except US): AKZO NOBEL N.V. [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): JONES, William [GB/GB]; 56, Lantree Crescent, Cambridge CB2 2NJ (GB). STAMIRES, Dennis [US/US]; 3401 Colony Plaza, Newport Beach, CA 92660 (US). O'CONNOR, Paul [NL/NL]; Hogebrinkerweg 9, NL-3871 KM Hoevelaken (NL). BRADY, Michael [US/US]; 4248 Rhodes Avenue, Studio City, CA 91604 (US).

- (74) Agent: SCHALKWIJK, Pieter, Cornelis; Akzo Nobel N.V., Intellectual Property Department (Dept. AIP), P.O. Box 9300, NL-6800 SB Arnhem (NL).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

## Published:

 without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR THE PREPARATION OF AN OXIDIC CATALYST COMPOSITION COMPRISING A DIVALENT AND A TRIVALENT METAL

(57) Abstract: Process for the preparation of an oxidic catalyst composition consisting of one or more trivalent metals, one or more divalent metals and - calculated as oxide and based on the total composition - more than 18 wt% of one or more compounds selected from the group consisting of rare earth metal compounds, phosphorus compounds, and transition metal compounds, which process comprises the steps of (a) preparing a precursor mixture consisting of (i) a compound 1 being one or more trivalent metal compounds, (ii) a compound 2 being one or more divalent metal compounds, (iii) a compound 3 which is different from compounds 1 and 2 and is one or more compounds selected from the group consisting of rare earth metal compounds phosphorus compounds, and transition metal compounds, and (iv) optionally water, which precursor mixture is not a solution, (b) if the precursor mixture contains water, optionally changing the pH of the slurry, (c) optionally aging the precursor mixture, (d) drying the precursor mixture when this mixture contains water and/or aging step c) is performed, and (e) calcining the resulting product. The resulting oxidic catalyst composition is suitable as a metal trap and SOx sorbent FCC processes.

